






PROCESS AND AQUEOUS SOLUTION FOR PHOSPHATISING METALLIC SURFACES

Patent number: EP0922123
Publication date: 1999-06-16
Inventor: KOLBERG THOMAS (DE); SCHUBACH PETER (DE)
Applicant: METALLGESELLSCHAFT AG (DE)
Classification:
- international: **C23C22/12; C23C22/18; C23C22/05; (IPC1-7): C23C22/12; C23C22/18**
- european: **C23C22/12; C23C22/18B; C23C22/18B2; C23C22/18E**
Application number: EP19970943803 19970811
Priority number(s): DE19961034685 19960828; WO1997EP04360 19970811

Also published as:

 WO9808999 (A1)
 US6261384 (B1)
 DE19634685 (A1)
 BR9713177 (A)
 EP0922123 (B1)

more >>

[Report a data error here](#)

Abstract not available for EP0922123

Abstract of corresponding document: **US6261384**

A process is disclosed for preparing an aqueous zinc phosphatizing solution for producing phosphate coatings on metallic surfaces of iron, steel, zinc, zinc alloys, aluminum or aluminum alloys, which comprises: (1) 0.3 to 5 g Zn²⁺/l; (2) 0.1 to 3 g nitroguanidine/l as an accelerator; (3) phosphate where the acid value is 0.03 to 0.3 indicating the ratio of free acid, calculated as free P₂O₅ to the total P₂O₅, and the weight ratio of Zn to P₂O₅ is 1:5 to 1:30; and (4) balance water, where the solution produces finely crystallite phosphate coatings in which the crystallites have a maximum edge length <15 µm, which comprises the steps of: (a) preparing a concentrate comprising the Zn²⁺ and the phosphate in water; (b) supplying additional water to the concentrate so that the Zn²⁺ concentration in the phosphatizing solution is 0.3 to 5 g/l; (c) preparing a stabilized suspension consisting essentially of 100 to 300 g of nitroguanidine/l, 10 to 30 g of sheet silicate/l as stabilizer and the balance water by suspending the sheet silicate in deionized water and stirring the nitroguanidine into the suspension; and (d) introducing the stabilized suspension into the phosphatizing solution so that the nitroguanidine concentration in the phosphatizing solution is 0.1 to 3 g nitroguanidine/liter.

Data supplied from the **esp@cenet** database - Worldwide